

How To Use Nanolex Professional Paint & Alloy Sealant

This product can be stored for up to 24 months (in a dry, temperature stable environment)

Consumption:

Cleaner: appr. 10ml/m² (~70 ml for paint + alloys)

Sealant: appr. 5ml/m² (~40 ml for paint + alloys)

Processing temperature: 5-30°C - Avoid direct sunlight and/or high air humidity.

IMPORTANT: Before you use a Nanolex Car Care product please make sure you wear suitable protection gear – we always recommend to use Nitril gloves to make sure your hands are protected from any possible damage to your skin.

1.1 Nanolex Professional Paint & Alloy can be applied directly to all clearcoated (lacquered) surfaces. The lacquer surface must be dry and free of any contamination or dust. We strongly recommend to use Nanolex EX directly before the application to make sure that all oils/fillers and other dirt are removed completely from the surface. Use Nanolex microfiber towels and turn or exchange cloth frequently during cleaning/polishing.

1.2 If the car was machine polished before the application it is absolutely necessary to remove any (mostly invisible) fillers and oils – if those are not removed a white or grey hazing will appear on the paint once the sealant was applied. The paint sealant layer itself is too thin to be visible and can easily buffed off – only fillers and oils will become visible.

2. Shake bottle before use! Spread approx. 6-8 sprays or 15-20 drops/m² of Nanolex Professional Paint & Alloy on an applicator pad (we recommend standard cotton makeup pads) and apply it sparingly by rubbing in with light pressure and permanent circular movements. Apply the product panel by panel. Buff off the sealant residue after 2-5 minutes with a soft microfiber cloth.

3. Let the product cure on the surface for at least 12 hours before the first water contact. Do not wash the car within the first 72 hours.

Please read the separate information on how to clean your car and wheels after a treatment with Nanolex Paint & Alloy Wheel sealants.

If you have any questions regarding our products or in case you need support during the application please feel free to get in touch with our staff any time.

The information on this data sheet is based on the current status of technical development as well as our experience with the product. However, given the variety of surfaces and ambient conditions, the information provided on this data sheet shall in no way diminish the responsibility of the user to ensure with due care, that our product is suited for the intended purpose, surface and application conditions. Since application and processing lie outside our purview, no manufacturer liability shall be derived from the information provided herein. Our General Terms and Conditions of business shall apply in all cases. All information is subject to change without notice.